



SILIRUB 989

(New Generation Weather Sealant)

(Developed for India)

Revision: 01/02/2016

Page 1 of 2

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation	25 - 30 min
Curing speed * (20°C / 65% R.H.)	Ca. 2 mm/24h
Hardness	35 ± 5 Shore A
Density	Ca. 1,45 g/ml
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	25 %
Temperature resistance	-60 °C → 180 °C
Max. tension (DIN 53504)	1,60 N/mm ²
Elasticity modulus 100% (DIN 53504)	0,60 N/mm ²
Elongation at break (DIN 53504)	Ca. 500 %
Application temperature	5 °C → 35 °C

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Silirub J1 J is a high performance, low odor, one-component joint and glazing sealants, based on neutral silicone. Silirub J1 J has been developed for weather sealing of joints in the façade and roof.

- Excellent for double glazing system applications

Packaging

Colour: white, black, grey

Packaging: 405g cartridge, 810g sausage

Properties

- Long open time
- Compatible with PVB-film
- Compatible with sealants for double glazing based on polysulphides and silicones
- Very easy to apply
- Colourfast and UV resistant
- Permanent elastic after curing
- Very good adhesion on many materials
- Corrosion free
- Resistant against UV-radiation, rain, frost, wind, ozone and extreme temperatures
- Excellent adhesion properties on glass, laminated glass, coated aluminium, galvanised steel, concrete and masonry

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: all usual building substrates

Nature: clean, dry, free of dust and grease.

Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. No primer needed for non-porous substrates.

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary compatibility test. Due to the wide variety materials used in façade technology a preliminary compatibility test is necessary.

Applications

- Weatherseal in curtain wall applications
- All usual building, connection, expansion and dilatation joints

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

McCoy Soudal Sealants Adhesives & Foams Pvt. Ltd.

McCoy Corporate Tower, C-55, Okhla Industrial Area, Phase-1, New Delhi - 110020 (INDIA)

Tel.: +91 11 40623344 (100 lines) | Fax: +91 11 40623355

Website: www.mccoysoudal.com | Email: info@mccoysoudal.com

1800-121-6569 (Toll Free)



SILIRUB 989

(New Generation Weather Sealant)

(Developed for India)

Revision: 01/02/2016

Page 2 of 2

Joint dimensions

Glazing and window applications: top sealing = minimum width 4 mm, depth at least 6 mm. Minimum joint width for connection joints around windows: 10 mm. Weatherseal and other applications: joint width 5 - 10 mm: joint depth 5 mm. Joint width 10 - 30 mm: depth = 1/2*width.

Application method

Application method: With manual- or pneumatic caulking gun

Cleaning: Clean with white spirit or Surface Cleaner immediately after use

Finishing: With a soapy solution or Soudal Finishing Solution before skinning

Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remarks

- Not suitable for structural glazing applications
- Do not use on natural stones like marble, granite,...(staining). Use Soudal Silirub MA
- The use of Soudal Surface Activator is recommended in combination with powder coated aluminium
- A total absence of UV can cause a color change of the sealant
- In an acid environment or in a dark room, white silicone can slightly turn yellow. Under the influence of sunlight it will turn back to its initial colour
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution
- We strongly recommend not to apply the product in full sunlight as it will dry very fast

- Do not use in applications where continuous water immersion is possible
- Do not use on polycarbonate. Use Silirub PC or Silirub AL instead

Standards

- Meets ISO 11600 G 25 HM

Environmental clauses

Lead regulation:

Silirub 989 conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. She is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

McCoy Soudal Sealants Adhesives & Foams Pvt. Ltd.

McCoy Corporate Tower, C-55, Okhla Industrial Area, Phase-1, New Delhi - 110020 (INDIA)

Tel.: +91 11 40623344 (100 lines) | Fax: +91 11 40623355

Website: www.mccoysoudal.com | Email: info@mccoysoudal.com

1800-121-6569 (Toll Free)