

Silirub MA

Revision: 1/06/2012

Page 1 from 2

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 5 min
Curing speed * (20°C / 65% R.H.)	Ca. 2 mm/24h
Hardness	25 ± 5 Shore A
Density	Ca. 1,25 g/ml
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	25 %
Temperature resistance	-60 °C → 180 °C
Max. tension (DIN 53504)	1,40 N/mm ²
Elasticity modulus 100% (DIN 53504)	0,40 N/mm ²
Elongation at break (DIN 53504)	600 %
Application temperature	5 °C → 35 °C

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Silirub MA is a high-quality, neutral, elastic one-component silicone based joint sealant.

Properties

- No staining on porous surfaces such as marble, granite and other natural stones
- Impervious to mould
- Very easy to apply
- Colourfast and UV resistant
- Permanent elastic after curing
- Very good adhesion on many materials
- Low modulus

Applications

- Sealing of joints that are in contact with natural stones (marble, blue stone, granite, ...) or other porous surfaces
- Sealing of joints in sanitary areas and kitchens which are in contact with natural stones.
- Expansion joints between many different construction materials.
- Top sealing in glazing.

Packaging

Colour: transparent, white, black, jasmine, stonegrey, natural stone, travertin, marbledgrey, RAL7016 (anthracite grey)
Packaging: 310 ml cartridge

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: all usual building substrates
Nature: clean, dry, free of dust and grease.
Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. No primer needed for non-porous substrates.
There is no adhesion on PE, PP, PTFE (Teflon®), silicones and bituminous substrates.
We recommend a preliminary compatibility test.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub MA

Revision: 1/06/2012

Page 2 from 2

Compatibility with glass

Silirub MA is not suitable for contact with secondary sealant of insulating glass units. Silirub MA is not suitable for applications in direct contact with PVB films of laminated glass, for this we recommend to use Silirub 2.

Joint dimensions

Min. width for joints: 5 mm
Max. width for joints: 30 mm
Min. depth for joints: 5 mm
Recommendation sealing jobs: joint width = 2 x joint depth.

Application method

Application method: With manual- or pneumatic caulking gun.
Cleaning: Clean with white spirit or Surface Cleaner immediately after use.
Finishing: With a soapy solution or Soudal Finishing Solution before skinning.
Repair: With the same material

Health- and Safety Recommendations

Take into account the usual labour hygiene. Consult the label for more information.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.