



SILICONIZED CS+

(New Generation Construction Sealant)

Revision: 01/06/2017

Page 1 of 2

Technical Data:

Consistency	Paste
Curing System	Physical drying
Skin formation (20°C/65% R.H.)	Approx. 20 min.
Shrinkage (DIN 52451)	Approx. 15%
Specific Gravity (DIN 53479B)	1,69g/ml
Temperature Resistance	-20°C to +80°C
Maximum allowed Distortion	±12.5%
Maximum gap filling capacity	6mm
Joints with movements up to	±12.5%

* This varies according to ambient conditions such as temperature, humidity, substrate etc.

Product:

Siliconized CS+ is a high quality single-component siliconized joint sealant.

Surfaces:

Type: all porous building surfaces

State of Surface: clean, dry, free of dust and grease

Characteristics:

- Maximum gap filling capacity 6mm
- Paintable
- Very good adhesion on porous surfaces, aluminium & wood

We recommend a preliminary compatibility test

Joint Size:

Maximum gap filling capacity: 6mm

Applications:

- Joints with movements up to ±12.5%
- Connection joints in the building industry
- Joints between windowsills, between skirting-board and floor, between brickwork, etc
- Not suitable for glass & mirrors

Applying the sealant:

Method: Apply the sealant by means of a handheld or pneumatic caulking gun. Smoothen the sealant with a filling-knife

Application temperature: +5°C to +30°C, do not apply when rain or frost are imminent

Clean: Uncured Siliconized CS+ can be removed from tools with water. Cured sealant must be removed mechanically

Finishing: with water

Packaging:

Colour: white,

Packaging: cartridge 450g

Shelf life and storage:

12 months from date of manufacturing in unopened packaging stored in a cool and dry place at recommended temperatures between +5°C and +25°. Protect against frost

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

McCoy Soudal Sealants Adhesives & Foams Pvt. Ltd.

McCoy Corporate Tower, C-55, Okhla Industrial Area, Phase-1, New Delhi - 110020 (INDIA)

Tel.: +91 11 40623344 (100 lines) | Fax: +91 11 40623355

Website: www.mccoysoudal.com | Email: info@mccoysoudal.com

1800-121-6569 (Toll Free)



SILICONIZED CS+ **(New Generation Construction Sealant)**

Revision: 01/06/2017

Page 2 of 2

Health- and safety recommendations:

Apply the usual industrial hygiene
Consult the label for more information

Remarks:

- Do not use in applications where continuous water immersion is possible
- Do not apply when rain or frost is imminent
- The paint should be sufficiently elastic to be applied on a plasto-elastic sealant. A preliminary test is recommended
- Siliconized CS+ can be painted over with most paints
- Not suitable for glass & mirrors

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

McCoy Soudal Sealants Adhesives & Foams Pvt. Ltd.

McCoy Corporate Tower, C-55, Okhla Industrial Area, Phase-1, New Delhi - 110020 (INDIA)

Tel.: +91 11 40623344 (100 lines) | Fax: +91 11 40623355

Website: www.mccoysoudal.com | Email: info@mccoysoudal.com

1800-121-6569 (Toll Free)