



## ACRYRUB EXTERIOR

Issue: 01/05/2018

Page 1 of 2

**Technical Data:**

Base	Siliconized Acrylic Dispersion
Consistency	Paste
Curing System	Moisture Cure
Skin formation (20°C/65% R.H.)	Ca 20 - 30 min.
Shrinkage (DIN 52451)	≤15%
Temperature Resistance	-20°C to +80°C
Maximum allowed Distortion	15% - 20%

\* This varies according to ambient conditions such as temperature, humidity, substrate etc.

**Product:**

Acryrub Exterior is a high-quality, plasto-elastic, one-component joint sealant based on siliconized acrylic dispersions. Developed for both interior and exterior applications.

**Characteristics:**

- Interior & exterior purpose
- Excellent crack bridging properties
- Excellent adhesion to most of the substrates including uPVC, aluminium, wood, metals, concrete, steel, and masonries
- Perimeter sealing
- Excellent movement capability
- Good UV resistance
- Paintable sandable

**Applications:**

- Joints with movements up to 15% - 20%.
- Sealing compound for cracks in concrete and plaster
- Connection joints in the building industry
- Joints between windowsills (uPVC, aluminium & wood), between skirting skirting board and floor, between brickwork, etc.

**Important note:**

One surface should be porous while applying Acryrub exterior.

**Packaging:**

Colour: white

Packaging: cartridge 425g, sausage 425g & 850g

**Shelflife:**

At least 12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +35°. Protect against frost!

**Not suitable for:**

- Natural stone
- Structural glazing
- Mirrors
- Glass to glass
- Automotive applications

**Joint Size:**

Minimum Width: 5mm

Maximum Width: 20mm

Minimum Depth: 5mm

Recommandation: jointh depth = joint width

Use PE backer rods in case of large joint dimensions to avoid three-sided adhesion

**Applying the sealant:**

*Method:* Apply the sealant by means of a handheld or pneumatic caulking gun. Smoothen the sealant with a filling-knife.

*Application temperature:* +5°C to +35°C, do not apply when rain or frost are imminent

*Clean:* Uncured Acryrub Exterior may be removed from tools with water. Cured sealant must be removed mechanically.

*Finishing:* with water

*Repair:* with Acryrub Exterior

**Remark:** The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

**McCoy Soudal Sealants Adhesives & Foams Pvt. Ltd.**

McCoy Corporate Tower, C-55, Okhla Industrial Area, Phase-1, New Delhi - 110020 (INDIA)

Tel.: +91 11 40623344 (100 lines) | Fax: +91 11 40623355

Website: www.mccoysoudal.com | Email: info@mccoysoudal.com

**1800-121-6569 (Toll Free)**



---

## ACRYRUB EXTERIOR

---

Issue: 01/05/2018

Page 2 of 2

**Remarks:**

- Do not use in applications where continuous water immersion is possible.
- Do not apply when rain or frost is imminent
- Acryrub Exterior can be painted over with most paints.
- The paint should be sufficiently elastic to be applied on a plasto-elastic sealant. A preliminary test is recommended.

**Health- and safety recommendations:**

Apply the usual industrial hygiene.  
Consult the label for more information

**Remark:** The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

---

**McCoy Soudal Sealants Adhesives & Foams Pvt. Ltd.**

McCoy Corporate Tower, C-55, Okhla Industrial Area, Phase-1, New Delhi - 110020 (INDIA)

Tel.: +91 11 40623344 (100 lines) | Fax: +91 11 40623355

Website: [www.mccoysoudal.com](http://www.mccoysoudal.com) | Email: [info@mccoysoudal.com](mailto:info@mccoysoudal.com)

**1800-121-6569 (Toll Free)**